



## ТАБЛИЦА СТОЙКОСТИ РЕЗИНОВЫХ ПЛАСТИН К РАЗЛИЧНЫМ ХИМИЧЕСКИМ ВЕЩЕСТВАМ

	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPDM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
<b>SP TECH®</b>											
Acetaldehyde	2	3	1	1	4	3	3	4	2	4	3
Acetamide	4	2	1	1	1	2	2	4	2	2	1
Acetic Acid, Glacial	2	2	2	1	1	4	3	4	2	3	3
Acetic Acid, 30%	2	2	2	1	2	1	2	4	1	2	1
Acetic Anhydride	2	2	2	2	3	2	1	4	3	4	4
<b>SP TECH®</b>											
Acetone	3	3	1	1	4	3	2	4	3	4	4
Acetophenone	4	4	1	1	4	4	4	4	4	4	4
Acetyl Chloride	4	4	4	4	4	4	4	4	3	1	1
Acetylene	2	2	1	1	1	2	2	4	2	1	1
Acrylonitrile	4	4	4	4	2	4	3	4	4	3	4
<b>SP TECH®</b>											
Adipic Acid	1	1	1	1	1	1	@	@	@	1	1
Alkazene (Dibromoethylbenzene)	4	4	4	4	4	4	4	4	4	2	2
Alum-NH3-Cr-K (aq)	1	1	1	1	1	1	1	@	1	4	@
Aluminum Acetate (aq)	1	2	1	1	2	2	1	4	4	4	4
Aluminum Chloride (aq)	1	1	1	1	1	1	1	3	2	1	1
<b>SP TECH®</b>											
Aluminum Fluoride (aq)	2	1	1	1	1	1	1	3	2	1	1
Aluminum Nitrate (aq)	1	1	1	1	1	1	1	3	2	1	1
Aluminum Phosphate (aq)	1	1	1	1	1	1	1	@	1	1	1
Aluminum Sulfate (aq)	1	1	1	1	1	1	1	4	1	1	1
Ammonia Anhydrous	4	4	1	1	2	1	2	4	3	4	4
<b>SP TECH®</b>											
Ammonia Gas (cold)	1	1	1	1	1	1	1	3	1	4	4
Ammonia Gas (hot)	4	4	2	2	4	2	2	4	1	4	4
Ammonium Carbonate (aq)	1	1	1	@	4	1	@	4	@	1	1

**SP TECH®**

**1** - рекомендовано

**2** - умеренное возд.

**3** - только в статике

**4** - не рекомендовано

@ - нет данных



	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPDM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
<b>SP TECH®</b>											
Ammonium Chloride (aq)	1	1	1	1	1	1	1	1	@	1	1
Ammonium Hydroxide (conc.)	1	1	1	1	1	1	1	1	1	2	1
Ammonium Nitrate (aq)	3	@	1	1	1	1	1	4	@	1	1
Ammonium Nitrite (aq)	1	1	1	1	1	1	1	@	2	1	1
Ammonium Persulfate (aq)	1	4	1	1	4	1	1	4	@	1	1
<b>SP TECH®</b>											
Ammonium Phosphate (aq)	1	1	1	1	1	1	1	@	1	1	1
Ammonium Sulfate (aq)	1	1	1	1	1	1	1	1	@	2	1
Amyl Acetate (Banana Oil)	4	4	3	3	4	4	4	4	4	4	4
Amyl Alcohol	2	2	1	1	2	2	1	4	4	2	1
Amyl Borate	4	4	4	4	1	1	1	@	@	1	1
<b>SP TECH®</b>											
Amyl Chloronapthalene	4	4	4	4	4	4	4	4	4	1	1
Amyl Napthalene	4	4	4	4	4	4	4	4	4	@	@
Aniline	4	4	1	1	4	4	3	4	4	3	1
Aniline Dyes	2	2	2	1	4	2	2	4	3	2	1
Aniline Hydrochloride	2	4	2	2	2	4	4	4	4	2	1
<b>SP TECH®</b>											
Animal Fats	4	4	2	2	1	2	2	1	2	1	1
Ansul Ether (Anesthetics)	4	4	3	3	3	4	4	2	4	4	4
Aqua Regia	3	4	4	3	4	4	2	4	4	2	1
Aroclor, 1248	4	4	3	3	3	4	1	4	2	1	1
Aroclor, 1254	4	4	4	3	4	4	4	4	3	4	1
<b>SP TECH®</b>											
Aroclor, 1260	1	1	1	1	1	1	1	4	2	1	1
Arsenic Acid	2	1	1	1	1	1	1	3	1	1	1
Arsenic Trichloride (aq)	4	4	3	3	1	1	@	@	@	4	4
Askarel	4	4	4	4	2	4	4	4	4	1	1
Asphalt	4	4	4	4	2	2	2	2	4	1	1

**SP TECH®**

**1** - рекомендовано

**2** - умеренное возд.

**3** - только в статике

**4** - не рекомендовано

@ - нет данных



	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPDM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
SP TECH®											
Banana Oil (Amyl Acetate)	4	4	3	3	4	4	4	4	4	4	4
Barium Chloride (aq)	1	1	1	1	1	1	1	1	1	1	1
Barium Hydroxide (aq)	1	1	1	1	1	1	1	4	1	1	1
Barium Sulfate (aq)	1	1	1	1	1	1	1	1	1	1	1
Barium Sulfide (aq)	1	2	1	1	1	1	1	1	1	1	1
SP TECH®											
Beer	1	1	1	1	1	1	1	2	1	1	1
Beet Sugar Liquors	1	1	1	1	1	2	1	4	1	1	1
Benzaldehyde	4	4	1	1	4	4	1	4	2	4	4
Benzene	4	4	4	4	4	4	4	3	4	1	1
Benzene Sulfonic Acid	4	4	4	3	4	2	1	4	4	1	1
SP TECH®											
Benzine (Ligroin)	4	4	4	4	1	3	2	2	4	1	1
Benzoic Acid	4	4	4	3	3	4	4	4	3	1	1
Benzoyl Chloride	4	4	4	4	4	4	4	@	@	2	1
Benzyl Alcohol	4	4	1	1	4	2	2	4	2	1	1
Benzyl Benzoate	4	4	2	2	4	4	4	@	@	1	1
SP TECH®											
Benzyl Chloride	4	4	4	4	4	4	4	4	4	1	1
Biphenyl (Diphenyl) (Phenylbenzene)	4	4	4	4	4	4	4	4	4	1	1
Blast Furnace Gas	4	4	4	4	4	4	4	4	1	1	1
Bleach Solutions	4	4	1	1	4	4	1	4	2	1	1
Borax	2	2	1	1	2	1	1	1	2	1	1
SP TECH®											
Bordeaux Mixture	2	2	1	1	2	2	1	4	2	1	1
Boric Acid	1	1	1	1	1	1	1	1	1	1	1
Brine	1	1	1	1	1	1	1	2	1	1	1
Bromine-Anhydrous	4	4	4	4	4	4	4	4	4	1	1
Bromine Trifluoride	4	4	4	4	4	4	4	4	4	4	4

SP TECH®

1 - рекомендовано   
 2 - умеренное возд.   
 3 - только в статике   
 4 - не рекомендовано   
 @ - нет данных



	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPDM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
SP TECH®											
Bromine Water	4	4	3	@	1	4	1	4	4	1	1
Bromobenzene	4	4	4	4	4	4	4	4	4	1	1
Bunker Oil	4	4	4	4	1	4	4	2	2	1	1
Butadiene	4	4	4	3	4	4	3	4	4	1	1
Butane	4	4	4	4	1	1	2	1	4	1	1
SP TECH®											
Butter (Animal Fat)	4	4	2	1	1	2	2	1	2	1	1
Butyl Acetate	4	4	3	3	4	4	4	4	4	4	4
Butyl Acetyl Ricinoleate	4	4	1	1	3	2	2	4	@	1	1
Butyl Acrylate	4	4	4	4	4	4	4	@	@	4	4
Butyl Alcohol	1	1	2	2	1	1	1	4	2	1	1
SP TECH®											
Butyl Amine	4	4	3	2	3	4	4	4	4	4	4
Butyl Benzoate	3	2	2	2	4	4	4	@	@	1	1
Butyl Carbitol	4	4	1	1	4	3	2	@	4	3	2
Butyl Cellosolve	4	4	1	1	3	3	2	4	@	4	4
Butyl Oleate	4	4	2	2	4	4	4	@	@	1	1
SP TECH®											
Butyl Stearate	4	4	3	3	2	4	4	@	@	1	1
Butylene	4	4	4	4	1	3	4	4	4	1	1
Butyraldehyde	4	4	2	2	4	3	4	4	4	4	4
Calcium Acetate (aq)	1	4	1	1	2	2	2	4	4	4	4
Calcium Bisulfite (aq)	4	4	4	4	4	1	1	1	1	1	1
SP TECH®											
Calcium Chloride (aq)	1	1	1	1	1	1	1	1	1	1	1
Calcium Hydroxide (aq)	1	1	1	1	1	1	1	1	1	1	1
Calcium Hypochlorite (aq)	3	3	1	1	2	3	1	4	2	1	1
Calcium Nitrate (aq)	1	1	1	1	1	1	1	1	2	1	1
Calcium Sulfide (aq)	2	2	1	1	1	1	1	1	2	1	1

SP TECH®

1 - рекомендовано

2 - умеренное возд.

3 - только в статике

4 - не рекомендовано

@ - нет данных



	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPDM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
SP TECH®											
Cane Sugar Liquors	1	1	1	1	1	1	1	4	@	1	1
Carbamate	4	4	1	2	3	2	2	4	1	1	1
Carbitol	2	2	2	2	2	2	2	4	2	2	2
Carbolic Acid (Phenol)	4	4	1	1	4	3	4	3	4	1	1
Carbon Bisulfide	4	4	4	4	3	4	4	@	4	1	1
SP TECH®											
Carbon Dioxide	2	2	2	2	1	2	2	1	2	1	1
Carbonic Acid	1	2	2	2	2	1	1	1	1	1	1
Carbon Monoxide	2	2	1	1	1	2	2	1	1	1	1
Carbon Tetrachloride	4	4	4	4	3	4	4	4	4	1	1
Castor Oil	1	1	2	2	1	1	2	1	1	1	1
SP TECH®											
Cellosolve	4	4	2	2	4	4	4	4	4	2	1
Cellosolve Acetate	4	4	2	2	4	4	4	4	4	1	1
Cellulube (Fryquel)	4	4	1	1	4	4	4	4	1	1	1
China Wood Oil (Tung Oil)	4	4	3	3	1	2	3	3	4	1	1
Chlorine (Dry)	4	4	4	4	4	3	2	4	4	1	1
SP TECH®											
Chlorine (Wet)	4	4	3	3	4	3	3	4	4	1	1
Chlorine Dioxide	4	4	3	3	4	4	3	4	@	1	1
Chlorine Trifluoride	4	4	4	4	4	4	4	4	4	1	1
Chloroacetic Acid	4	4	2	1	4	4	1	4	@	1	1
Chloroacetone	4	4	2	1	4	3	3	4	4	1	1
SP TECH®											
Chlorobenzene	4	4	4	4	4	4	4	4	4	1	1
Chlorobromomethane	4	4	2	2	4	4	4	4	4	1	1
Chlorobutadiene	4	4	4	4	4	4	4	4	4	1	1
Chlorododecane	4	4	4	4	4	4	4	4	4	1	1
Chloroform	4	4	4	4	4	4	4	4	4	1	1

SP TECH®

1 - рекомендовано

2 - умеренное возд.

3 - только в статике

4 - не рекомендовано

@ - нет данных



	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPDM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
SP TECH®											
O-Chloronaphthalene	4	4	4	4	4	4	4	4	4	1	1
1-Chloro-1-Nitro Ethane	4	4	4	4	4	4	4	4	4	4	4
Chlorosulfonic Acid	4	4	4	4	4	4	4	4	4	4	4
Chlorotoluene	4	4	4	4	4	4	4	4	4	1	1
Chlorox (Sodium Hypochlorite NaOC1)	4	4	2	2	2	1	2	4	2	1	1
SP TECH®											
Chrome Plating Solutions	4	4	2	2	4	4	4	4	2	1	1
Chromic Acid	4	4	3	3	4	3	2	4	3	1	1
Citric Acid	1	1	1	1	1	1	1	1	1	1	1
Coal Tar (Creosote)	4	4	4	4	1	2	4	3	4	1	1
Cobalt Chloride (aq)	1	1	1	1	1	1	1	4	2	1	1
SP TECH®											
Cocoonut Oil	4	4	3	3	1	2	3	2	1	1	1
Cod Liver Oil	4	4	1	1	1	2	2	1	2	1	1
Coke Oven Gas	4	4	4	4	4	4	3	4	2	1	1
Copper Acetate (aq)	1	4	1	1	2	2	2	4	4	4	4
Copper Chloride (aq)	1	1	1	1	1	2	2	1	1	1	1
SP TECH®											
Copper Cyanide (aq)	1	1	1	1	1	1	1	1	1	1	1
Copper Sulfate (aq)	2	2	2	1	1	1	1	1	1	1	1
Corn Oil	4	4	3	3	1	3	2	1	1	1	1
Cottonseed Oil	4	4	3	2	1	2	2	1	1	1	1
Creosote (Coal Tar)	4	4	4	4	1	2	4	3	4	1	1
SP TECH®											
Cresol	4	4	4	4	4	3	4	4	4	1	1
Cresylic Acid	4	4	4	4	4	3	4	4	4	1	1
Cumene	4	4	4	4	4	4	4	4	4	1	1
Cyclohexane	4	4	4	4	1	3	4	1	4	1	1
Cyclohexanol	4	4	4	3	3	1	2	@	4	1	1

SP TECH®

1 - рекомендовано    2 - умеренное возд.    3 - только в статике    4 - не рекомендовано    @ - нет данных



	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPDM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
SP TECH®											
Cyclohexanone	4	4	2	2	4	4	4	4	4	4	4
P-Cymene	4	4	4	4	4	4	4	4	4	1	1
Decalin	4	4	4	4	4	4	4	@	4	1	1
Decane	4	4	4	4	1	2	2	2	2	1	1
Denatured Alcohol	1	1	1	1	1	4	3	4	1	1	1
SP TECH®											
Detergent Solutions	2	2	1	1	1	4	4	4	1	1	1
Developing Fluids	1	2	2	2	1	1	@	@	1	1	1
Diacetone	4	4	1	1	4	4	4	4	4	4	3
Diacetone Alcohol	4	4	1	1	4	2	2	4	2	4	3
Dibenzyl Ether	4	4	2	2	4	3	4	2	@	4	4
SP TECH®											
Dibenzyl Sebecate	4	4	2	2	4	4	4	2	3	2	1
Dibromoethylbenzene (Alkazene)	4	4	4	4	4	4	4	4	4	2	1
Dibutyl Amine	4	4	4	3	4	4	4	4	3	4	4
Dibutyl Ether	4	4	3	3	4	3	4	2	4	3	3
Dibutyl Phthalate	4	4	3	2	4	4	4	3	2	3	1
SP TECH®											
Dibutyl Sebecate	4	4	2	2	4	4	4	4	2	2	1
O-Dichlorobenzene	4	4	4	4	4	4	4	4	4	1	1
Dichloro-Isopropyl Ether	4	4	4	3	4	4	4	2	4	3	3
Dicyclohexylamine	4	4	4	4	3	4	4	4	@	4	4
Diesel Oil	4	4	4	4	1	3	3	3	4	1	1
SP TECH®											
Diethylamine	2	2	2	2	2	2	3	3	2	4	4
Diethyl Benzene	4	4	4	4	4	4	4	4	4	1	1
Diethyl Ether	4	4	4	4	4	3	3	1	4	4	4
Diethylene Glycol	1	1	1	1	1	1	1	4	2	1	1
Diethyl Sebecate	4	4	2	2	2	4	2	4	2	2	1

SP TECH®

1 - рекомендовано

2 - умеренное возд.

3 - только в статике

4 - не рекомендовано

@ - нет данных



	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPDM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
SP TECH®											
Diisobutylene	4	4	4	4	2	4	4	4	4	1	1
Diisopropyl Benzene	4	4	4	4	4	4	4	@	@	1	1
Diisopropyl Ketone	4	4	1	1	4	4	4	4	4	4	4
Diisopropylidene Acetone (Phorone)	4	4	3	3	4	4	4	4	4	4	4
Dimethyl Aniline (Xylidine)	3	3	3	2	3	3	4	4	4	4	4
SP TECH®											
Dimethyl Ether (Methyl Ether) (Monomethyl Ether)	4	4	4	4	1	3	3	@	1	4	4
Dimethyl Formamide	4	4	2	2	2	3	4	4	2	4	4
Dimethyl Phthalate	4	4	2	2	4	4	4	@	@	2	1
Dinitrotoluene	4	4	4	4	4	4	4	4	4	4	4
SP TECH®											
Diethyl Phtalate	4	4	2	2	3	4	4	4	3	2	1
Diethyl Sebecate	4	4	2	2	4	4	4	2	3	2	1
Dioxane	4	4	2	2	4	4	4	4	4	4	4
Dioxolane	4	4	3	2	4	4	4	4	4	4	4
Dipentene	4	4	4	4	2	4	4	4	4	1	1
SP TECH®											
Diphenyl (Biphenyl) (Phenylbenzene)	4	4	4	4	4	4	4	4	4	1	1
Diphenyl Oxides	4	4	4	4	4	4	4	4	3	1	1
Dowtherm Oil	4	4	4	4	4	4	4	3	3	1	1
Dry Cleaning Fluids	4	4	4	4	3	4	4	4	4	1	1
Epichlorohydrin	4	4	2	2	4	4	4	4	4	4	4
SP TECH®											
Ethane	4	4	4	4	1	2	2	3	4	1	1
Ethanolamine	2	2	2	2	2	2	3	3	2	4	4
Ethyl Acetate	4	4	2	2	4	3	4	4	2	4	4
Ethyl Acetoacetate	3	3	2	2	4	3	4	4	2	4	4
Ethyl Acrylate	4	4	2	2	4	4	4	4	2	4	4

SP TECH®

1 - рекомендовано

2 - умеренное возд.

3 - только в статике

4 - не рекомендовано

@ - нет данных





	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPDM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
SP TECH®											
Ethyl Alcohol	1	1	1	1	1	1	1	4	1	2	1
Ethyl Benzene	4	4	4	4	1	4	4	4	4	1	1
Ethyl Benzoate	1	1	1	1	4	4	4	4	4	1	1
Ethyl Cellosolve	4	4	4	4	4	4	4	4	4	4	4
Ethyl Cellulose	2	2	2	2	2	2	2	2	3	4	4
SP TECH®											
Ethyl Chloride	4	4	4	3	1	4	4	2	4	1	1
Ethyl Chlorocarbonate	4	4	3	2	4	4	4	4	4	1	1
Ethyl Chloroformate	4	4	3	2	4	4	4	4	4	4	4
Ethyl Ether	4	4	3	3	3	3	4	3	4	4	4
Ethyl Formate	4	4	2	2	4	2	2	@	@	1	1
SP TECH®											
Ethyl Mercaptan	4	4	4	3	4	3	2	@	3	2	1
Ethyl Oxalate	1	1	1	1	4	3	4	1	4	1	1
Ethyl Pentachlorobenzene	4	4	4	4	4	4	4	4	4	1	1
Ethyl Silicate	2	2	1	1	1	1	2	@	@	1	1
Ethylene	3	3	2	2	1	3	@	@	@	1	1
SP TECH®											
Ethylene Chloride	4	4	3	3	4	4	4	4	4	2	1
Ethylene Chlorohydrin	2	2	2	2	3	2	2	4	3	1	1
Ethylene Diamine	1	2	1	1	1	1	2	4	1	4	4
Ethylene Dichloride	4	4	3	3	4	4	4	4	4	1	1
Ethylene Glycol	1	1	1	1	1	1	1	4	1	1	1
SP TECH®											
Ethylene Oxide	4	4	3	3	4	4	4	4	4	4	4
Ethylene Trichloride	4	4	3	3	4	4	4	4	4	1	1
Fatty Acids	4	4	3	3	2	2	2	@	3	1	1
Ferric Chloride (aq)	1	1	1	1	1	1	1	1	2	1	1
Ferric Nitrate (aq)	1	1	1	1	1	1	1	1	3	1	1

SP TECH®

1 - рекомендовано      2 - умеренное возд.      3 - только в статике      4 - не рекомендовано      @ - нет данных



	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPDM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
SP TECH®											
Ferric Sulfate (aq)	1	1	1	1	1	1	1	1	2	1	1
Fish Oil	4	4	4	4	1	4	@	@	1	1	1
Fluorinated Cyclic Ethers	4	4	1	1	@	4	@	@	@	@	2
Fluorine (Liquid)	4	4	4	4	4	4	@	4	4	2	1
Fluorobenzene	4	4	4	4	4	4	@	4	4	1	1
SP TECH®											
Fluoroboric Acid	1	1	1	1	1	1	1	@	@	@	2
Fluorocarbon Oils	2	2	1	1	@	2	@	@	@	@	2
Fluorolube	2	3	1	1	1	2	1	@	1	2	1
Fluorosilicic Acid (Hydrofluosilicic Acid)	2	3	2	2	1	2	1	@	4	1	1
SP TECH®											
Formaldehyde (RT)	2	2	1	1	3	2	1	4	2	4	4
Formic Acid	2	1	1	1	2	1	1	3	2	3	4
Freon 11	4	4	4	4	2	3	1	4	4	2	2
Freon 12	2	1	2	2	1	1	1	1	4	2	2
Freon 13	1	1	1	1	1	1	1	@	4	2	2
SP TECH®											
Freon 21	4	4	4	4	4	4	4	@	4	4	4
Freon 22	2	1	1	1	4	1	1	4	4	4	4
Freon 31	2	4	1	1	4	2	2	@	@	4	4
Freon 32	1	1	1	1	1	1	1	@	@	4	4
Freon 112	4	3	4	4	2	3	2	@	4	2	2
SP TECH®											
Freon 113	3	2	4	3	1	1	1	2	4	3	3
Freon 114	1	1	1	1	1	1	1	1	4	2	2
Freon 115	1	1	1	1	1	1	1	@	@	2	2
Freon 142b	2	2	1	2	1	1	1	@	@	4	4
Freon 152a	1	1	1	1	1	1	3	@	@	4	4

1 - рекомендовано

2 - умеренное возд.

3 - только в статике

4 - не рекомендовано

@ - нет данных

SP TECH®



	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPDM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
<b>SP TECH®</b>											
Freon 218	1	1	1	1	1	1	1	@	@	2	2
Freon C316	1	1	1	1	1	1	1	@	@	2	2
Freon C318	1	1	1	1	1	1	1	@	@	2	2
Freon 13B1	1	1	1	1	1	1	1	1	4	2	2
Freon 114B2	4	3	4	4	2	3	1	@	4	2	2
<b>SP TECH®</b>											
Freon 502	1	1	1	1	2	1	@	@	@	4	4
Freon TF	4	3	4	4	1	1	1	1	4	2	2
Freon T-WD602	4	3	2	2	2	2	2	1	4	2	2
Freon TMC	4	4	3	3	2	3	2	2	3	2	2
Freon T-P35	1	1	1	1	1	1	1	1	1	2	2
<b>SP TECH®</b>											
Freon TA	3	3	2	2	1	2	1	1	3	4	4
Freon TC	4	3	2	2	1	1	1	1	4	2	2
Freon MF	4	4	4	4	1	3	2	3	4	2	2
Freon BF	4	4	4	4	2	3	2	@	4	2	2
Fuel Oil	4	4	4	4	1	2	2	2	4	1	1
<b>SP TECH®</b>											
Fumaric Acid	3	3	2	2	1	2	2	@	2	1	1
Furan, Furfuran	4	4	4	3	4	4	4	@	@	4	4
Furfural	4	4	2	2	4	3	3	3	1	4	4
Fyrquel (Cellulube)	4	4	1	1	4	4	4	4	1	1	1
Gallic Acid	1	2	2	2	2	2	2	4	@	1	1
<b>SP TECH®</b>											
Gasoline	4	4	4	4	2	3	3	2	4	1	1
Gelatin	1	1	1	1	1	1	1	4	1	1	1
Glauber's Salt (aq)	2	4	2	2	4	2	2	@	@	1	1
Glucose	1	1	1	1	1	1	1	4	1	1	1
Glue	2	2	2	1	1	1	1	1	1	1	1

**SP TECH®**

1 - рекомендовано    
 2 - умеренное возд.    
 3 - только в статике    
 4 - не рекомендовано    
 @ - нет данных



	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPDM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
<b>SP TECH®</b>											
Glycerin	1	1	1	1	1	1	1	1	1	1	1
Glycols	1	1	1	1	1	1	1	4	1	1	1
Green Sulfate Liquor	2	2	1	1	2	2	2	1	1	1	1
Halowax Oil	4	4	4	4	4	4	4	@	4	1	1
N-Hexaldehyde	4	4	2	1	4	1	3	2	2	4	4
<b>SP TECH®</b>											
Hexane	4	4	4	4	1	2	2	2	4	1	1
N-Hexene-1	4	4	4	4	2	2	2	2	4	1	1
Hexyl Alcohol	2	2	3	3	1	2	2	4	2	1	1
Hydrazine	1	1	1	1	2	2	2	4	3	4	4
Hydraulic Oil (Petroleum)	4	4	4	4	1	2	2	1	3	1	1
<b>SP TECH®</b>											
Hydrobromic Acid	1	4	1	1	4	4	1	4	4	1	1
Hydrobromic Acid 40%	1	4	1	1	4	2	1	4	4	1	1
Hydrochloric Acid (Cold) 37%	2	4	1	1	3	2	1	4	3	1	1
Hydrochloric Acid (Hot) 37%	4	4	3	3	4	4	2	4	4	2	1
Hydrocyanic Acid	2	2	1	1	2	2	1	@	3	1	1
<b>SP TECH®</b>											
Hydrofluoric Acid (Conc.) Cold	4	4	3	3	4	4	1	3	4	1	1
Hydrofluoric Acid (Conc.) Hot	4	4	4	4	4	4	3	4	4	4	4
Hydrofluoric Acid-Anhydrous	4	4	3	3	4	4	1	4	4	4	4
Hydrofluosilicic Acid (Fluosilicic Acid)	2	3	2	2	1	2	1	@	4	1	1
<b>SP TECH®</b>											
Hydrogen Gas	2	1	1	1	1	1	1	1	3	1	1
Hydrogen Peroxide (90%)	4	4	3	2	4	4	1	@	2	2	1
Hydrogen Sulfide (Wet) Cold	4	4	1	1	4	2	2	@	3	4	3
Hydrogen Sulfide (Wet) Hot	4	4	1	1	4	3	3	@	3	4	3
Hydroquinone	2	4	2	2	3	4	4	@	@	2	1

**SP TECH®**

1 - рекомендовано

2 - умеренное возд.

3 - только в статике

4 - не рекомендовано

@ - нет данных



	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPDM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
SP TECH®											
Hypochlorous Acid	2	4	2	2	4	4	4	@	@	1	1
Iodine Pentafluoride	4	4	4	4	4	4	4	4	4	4	4
Iodoform	4	4	4	4	@	4	@	@	@	3	2
Isobutyl Alcohol	1	2	1	1	2	1	1	4	1	1	1
Isooctane	4	4	4	4	1	2	2	2	4	1	1
SP TECH®											
Isophorone	4	4	3	3	4	4	4	3	4	4	4
Isopropyl Acetate	4	4	2	2	4	4	4	4	4	4	4
Isopropyl Alcohol	1	2	1	1	2	2	1	3	1	1	1
Isopropyl Chloride	4	4	4	4	4	4	4	4	4	1	1
Isopropyl Ether	4	4	4	4	2	3	3	2	4	4	4
SP TECH®											
Kerosene	1	1	1	1	1	2	1	1	1	1	1
Lacquers	4	4	4	4	4	4	4	4	4	4	2
Lacquer Solvents	4	4	4	4	4	4	4	4	4	4	4
Lactic Acid (Cold)	1	1	1	1	1	1	1	@	1	1	1
Lactic Acid (Hot)	4	4	4	4	4	4	3	@	2	1	1
SP TECH®											
Lard	4	4	2	2	1	2	1	1	2	1	1
Lavender Oil	4	4	4	4	2	4	4	4	4	1	1
Lead Acetate (aq)	1	4	1	1	2	2	4	4	4	4	4
Lead Nitrate (aq)	1	1	1	1	1	1	1	@	2	1	1
Lead Sulfamate (aq)	2	2	1	1	2	1	1	@	2	1	1
SP TECH®											
Ligroin (Benzene) (Nitrobenzine) (Pet Ether)	4	4	4	4	1	2	3	2	4	1	1
Lime Bleach	1	2	1	1	1	2	2	@	2	1	1
Lime Sulfur	4	4	1	1	4	1	1	@	1	1	1
Lindol (Hydraulic Fluid)	4	4	1	1	4	4	4	4	3	2	1

SP TECH®

1 - рекомендовано

2 - умеренное возд.

3 - только в статике

4 - не рекомендовано

@ - нет данных



	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPDM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
<b>SP TECH®</b>											
Linoleic Acid	4	4	4	4	2	4	4	@	2	2	1
Linseed Oil	4	4	3	3	1	2	2	2	1	1	1
Liquefied Petroleum Gas	4	4	4	4	1	2	2	1	3	1	1
Lubricating Oils (Petroleum)	4	4	4	4	1	2	2	2	4	1	1
Lye	2	2	1	1	2	2	1	4	2	2	1
<b>SP TECH®</b>											
Magnesium Chloride (aq)	1	1	1	1	1	1	1	1	1	1	1
Magnesium Hydroxide (aq)	2	2	1	1	2	1	1	4	@	1	1
Magnesium Sulfate (aq)	2	2	1	1	1	1	1	@	1	1	1
Maleic Acid	3	3	2	2	4	3	4	@	@	1	1
Maleic Anhydride	3	3	2	2	4	3	4	@	@	4	3
<b>SP TECH®</b>											
Malic Acid	3	3	2	2	1	3	2	@	2	1	1
Mercury Chloride (aq)	1	1	1	1	1	1	1	@	@	1	1
Mercury	1	1	1	1	1	1	1	1	@	1	1
Mesityl Oxide	4	4	2	2	4	4	4	4	4	4	4
Methane	4	4	4	4	2	2	2	3	4	1	1
<b>SP TECH®</b>											
Methyl Acetate	3	3	1	1	2	4	4	4	4	4	4
Methyl Acrylate	4	4	2	2	2	4	4	4	4	4	4
Methylacrylic Acid	4	4	2	2	2	4	4	4	4	4	4
Methyl Alcohol	1	1	1	1	1	1	1	4	1	4	1
Methyl Bromide	4	4	4	4	4	4	4	@	@	1	1
<b>SP TECH®</b>											
Methyl Butyl Ketone (Propyl Acetone)	4	4	1	1	4	4	4	4	3	4	4
Methyl Cellosolve	4	4	2	2	3	2	2	4	4	4	4
Methyl Chloride	4	4	3	3	4	4	4	4	4	2	1
Methyl Cyclopentane	4	4	4	4	4	4	4	4	4	1	1

**SP TECH®**

1 - рекомендовано    
 2 - умеренное возд.    
 3 - только в статике    
 4 - не рекомендовано    
 @ - нет данных



	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPDM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
<b>SP TECH®</b>											
Methylene Chloride	4	4	4	3	4	4	4	4	4	2	2
Methyl Ether (Dimethyl Ether)	4	4	4	4	3	3	3	@	1	4	4
Methyl Ethyl Ketone	4	4	2	1	3	4	4	4	4	4	4
Methyl Formate	4	4	2	2	2	2	2	@	@	4	4
Methyl Isobutyl Ketone	4	4	3	2	4	4	4	4	4	4	4
<b>SP TECH®</b>											
Methyl Methacrylate	4	4	4	3	4	4	4	@	4	4	4
Methyl Oleate	4	4	2	2	4	4	4	@	@	2	1
Methyl Salicylate	3	3	2	2	4	4	4	@	@	2	1
Milk	1	1	1	1	1	1	1	4	1	1	1
Mineral Oil	4	4	3	3	2	2	2	1	@	1	1
<b>SP TECH®</b>											
Monochlorobenzene	4	4	4	4	4	4	4	4	4	1	1
Monomethyl Aniline	4	4	2	2	4	4	4	4	@	2	2
Monoethanol Amine	2	2	2	1	4	4	4	4	2	4	4
Monomethyl Ether (Methyl Ether) (Dimethyl Ether)	4	4	4	4	3	2	2	@	1	4	4
<b>SP TECH®</b>											
Monovinyl Acetylene	2	2	2	2	2	2	2	@	2	1	1
Mustard Gas	1	2	1	1	1	1	1	@	1	1	1
Naphtha	4	4	4	4	3	4	4	2	4	1	1
Naphthalene	4	4	4	4	4	4	4	2	4	1	1
Naphthalenic Acid	4	4	4	4	4	4	4	@	4	1	1
<b>SP TECH®</b>											
Natural Gas	2	2	4	4	1	1	1	2	1	1	1
Neats Foot Oil	4	4	2	2	4	4	4	1	2	1	1
Neville Acid	4	4	2	2	4	4	4	@	4	1	1
Nickel Acetate (aq)	1	4	1	1	2	2	4	4	4	4	4
Nickel Chloride (aq)	1	1	1	1	1	1	1	3	1	1	1

**SP TECH®**

**1** - рекомендовано

**2** - умеренное возд.

**3** - только в статике

**4** - не рекомендовано

**@** - нет данных



	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPDM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
<b>SP TECH®</b>											
Nickel Sulfate (aq)	2	2	1	1	1	1	1	3	1	1	1
Niter Cake	1	1	1	1	1	1	1	1	1	1	1
Nitric Acid (Conc.)	4	4	4	4	4	4	2	4	4	2	1
Nitric Acid (Dilute)	4	4	2	2	4	2	1	3	2	1	1
Nitric Acid-Red Fuming	4	4	4	4	4	4	4	4	4	3	2
<b>SP TECH®</b>											
Nitrobenzene	4	4	1	1	4	4	4	4	4	2	1
Nitrobenzene (Petroleum Ether)	4	4	4	4	1	2	3	2	4	1	1
Nitroethane	2	2	2	2	4	3	2	4	4	4	4
Nitrogen	1	1	1	1	1	1	1	1	1	1	1
Nitrogen Tetroxide	4	4	3	3	4	4	4	4	4	4	4
<b>SP TECH®</b>											
Nitromethane	2	2	2	2	2	3	3	4	4	4	4
Octachlorotoluene	4	4	4	4	4	4	4	3	4	1	1
Octadecane	4	4	4	4	2	2	2	1	4	1	1
N-Octane	4	4	4	4	2	2	2	4	4	1	1
Octyl Alcohol	2	2	3	3	1	2	2	4	2	1	1
<b>SP TECH®</b>											
Oleic Acid	4	4	4	4	3	3	3	2	4	2	2
Oleum Spirits	4	4	4	4	3	2	2	3	4	1	1
Olive Oil	4	4	2	2	2	2	2	1	3	1	1
O-Dichlorobenzene	4	4	4	4	4	4	4	4	4	1	1
Oxalic Acid	2	2	1	1	2	2	2	@	2	1	1
<b>SP TECH®</b>											
Oxygen-Cold	2	2	1	1	1	1	1	1	1	1	1
Oxygen-(200-400°F)	4	4	4	3	4	4	4	4	2	2	1
Ozone	4	4	2	1	3	1	1	1	1	1	1
Paint Thinner, Duco	4	4	4	4	4	4	4	4	4	2	1
Palmitic Acid	2	2	2	2	2	3	3	1	4	1	1

**SP TECH®**

**1** - рекомендовано

**2** - умеренное возд.

**3** - только в статике

**4** - не рекомендовано

**@** - нет данных





	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPDM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
SP TECH®											
Peanut Oil	4	4	3	3	3	2	2	2	1	1	1
Perchloric Acid	4	4	2	2	2	2	2	4	4	1	1
Perchloroethylene	4	4	4	4	4	4	4	4	4	1	1
Petroleum-Below 250°F	4	4	4	4	2	2	2	2	2	1	1
Petroleum-Above 250°F	4	4	4	4	2	4	4	4	4	2	1
SP TECH®											
Phenol (Carbolic Acid)	4	@	2	2	3	2	2	3	4	1	1
Phenylbenzene (Biphenyl) (Diphenyl)	4	4	4	4	4	4	4	4	4	1	1
Phenyl Ethyl Ether	4	4	4	4	4	4	4	4	4	4	4
Phenyl Hydrazine	1	2	2	2	4	4	4	@	@	2	1
SP TECH®											
Phorone (Diisopropylidene Acetone)	4	4	3	3	4	4	4	4	4	4	4
Phosphoric Acid-20%	2	2	2	1	2	1	1	1	2	1	1
Phosphoric Acid-45%	3	3	2	1	2	2	2	1	3	1	1
Phosphorus Trichloride	4	4	1	1	4	4	4	@	@	1	1
SP TECH®											
Pickling Solution	4	4	3	3	4	2	2	4	4	2	1
Picric Acid	2	2	2	2	1	2	2	2	4	1	1
Pinene	4	4	4	4	3	3	3	2	4	1	1
Pine Oil	4	4	4	4	4	4	4	@	4	1	1
Piperidine	4	4	4	4	4	4	4	4	4	4	4
SP TECH®											
Plating Solution-Chrome	4	4	1	1	4	4	4	@	4	1	1
Plating Solution-Others	4	4	1	1	4	1	1	@	4	1	1
Polyvinyl Acetate Emulsion	2	4	1	1	2	2	2	@	@	@	1
Potassium Acetate (aq)	1	4	1	1	2	1	1	4	4	4	4
Potassium Chloride (aq)	1	1	1	1	1	1	1	1	1	1	1

SP TECH®

1 - рекомендовано

2 - умеренное возд.

3 - только в статике

4 - не рекомендовано

@ - нет данных



	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPDM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
<b>SP TECH®</b>											
Potassium Cupro Cyanide (aq)	1	1	1	1	1	1	1	1	1	1	1
Potassium Cyanide (aq)	1	1	1	1	1	1	1	1	1	1	1
Potassium Dichromate (aq)	2	2	1	1	1	1	1	2	1	1	1
Potassium Hydroxide (aq)	2	2	1	1	2	1	1	4	3	4	4
Potassium Nitrate (aq)	1	1	1	1	1	1	1	1	1	1	1
<b>SP TECH®</b>											
Potassium Sulfate (aq)	2	1	1	1	1	2	2	1	1	1	1
Producer Gas	4	4	4	4	2	2	2	1	2	1	1
Propane	4	4	4	4	2	2	2	3	4	1	1
i-Propyl Acetate	4	4	2	2	4	4	4	4	4	4	4
n-Propyl Acetate	<b>SP TECH®</b>										
Propyl Acetone (Methyl Butyl Ketone)	4	4	1	1	4	4	4	4	3	4	4
Propyl Alcohol	1	1	1	1	1	1	1	4	1	1	1
Propyl Nitrate	4	4	2	2	4	4	4	@	4	4	4
Propylene	4	4	4	4	4	4	4	4	4	1	1
<b>SP TECH®</b>											
Propylene Oxide	4	4	2	2	4	4	4	4	4	4	4
Pydraul, 10E, 29 ELT	4	4	1	1	4	4	4	4	4	1	1
Pydraul, 30E, 50E, 65E, 90E	4	4	1	1	4	4	4	4	1	1	1
Pydraul, 115E	4	4	1	1	4	4	4	4	4	1	1
Pydraul, 230E, 312C, 540C	4	4	4	4	4	4	4	4	4	1	1
<b>SP TECH®</b>											
Pyranol, Transformer Oil	4	4	4	4	1	2	3	2	4	1	1
Pyridine	4	4	2	2	4	4	4	@	4	4	4
Pyroligneous Acid	4	4	2	2	4	2	2	4	@	4	4
Pyrrole	3	3	4	3	4	4	4	4	2	4	4
Radiation	3	3	4	2	3	2	3	3	3	3	3

**SP TECH®**

**1** - рекомендовано

**2** - умеренное возд.

**3** - только в статике

**4** - не рекомендовано

@ - нет данных



	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPDM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
<b>SP TECH®</b>											
Rapeseed Oil	4	4	1	1	2	2	2	2	4	1	1
Red Oil (MIL-H-5606)	4	4	4	4	1	2	2	1	4	1	1
RJ-1 (MIL-F-25558 B)	4	4	4	4	1	2	2	1	4	1	1
RP-1 (MIL-F-25576 C)	4	4	4	4	1	2	2	1	4	1	1
Sal Ammoniac	1	1	1	1	1	1	1	1	2	1	1
<b>SP TECH®</b>											
Salicylic Acid	1	2	1	1	2	1	@	@	@	1	1
Salt Water	1	1	1	1	1	2	1	2	1	1	1
Sewage	2	2	2	2	1	2	1	4	2	1	1
Silicate Esters	4	4	4	4	2	1	1	1	4	1	1
Silicone Greases	1	1	1	1	1	1	1	1	3	1	1
<b>SP TECH®</b>											
Silicone Oils	1	1	1	1	1	1	1	1	3	1	1
Silver Nitrate	1	1	1	1	2	1	1	1	1	1	1
Skydrol 500	4	4	2	1	4	4	4	4	3	4	4
Skydrol 7000	4	4	1	1	4	4	4	4	3	2	1
Soap Solutions	2	1	1	1	1	2	1	3	1	1	1
<b>SP TECH®</b>											
Soda Ash	1	1	1	1	1	1	1	@	1	1	1
Sodium Acetate (aq)	1	4	1	1	2	2	1	4	4	4	4
Sodium Bicarbonate (aq) (Baking Soc	1	1	1	1	1	1	1	@	1	1	1
Sodium Bisulfite (aq)	1	2	1	1	1	1	1	@	1	1	1
Sodium Borate (aq)	1	1	1	1	1	1	1	@	1	1	1
<b>SP TECH®</b>											
Sodium Chloride (aq)	1	1	1	1	1	1	1	1	1	1	1
Sodium Cyanide (aq)	1	1	1	1	1	1	1	@	1	1	1
Sodium Hydroxide (aq)	1	1	1	1	2	1	1	4	2	2	1
Sodium Hypochlorite (aq) (Chlorox)	4	4	2	2	2	1	1	4	2	1	1

**SP TECH®**

1 - рекомендовано   
 2 - умеренное возд.   
 3 - только в статике   
 4 - не рекомендовано   
 @ - нет данных



	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPDM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
<b>SP TECH®</b>											
Sodium Metaphosphate (aq)	1	1	1	1	1	2	2	@	@	1	1
Sodium Nitrate (aq)	2	1	1	1	2	2	1	@	4	1	1
Sodium Perborate (aq)	2	2	1	1	2	2	2	@	2	1	1
Sodium Peroxide (aq)	2	2	1	1	2	2	@	4	4	2	1
Sodium Phosphate (aq)	1	1	1	1	1	2	1	1	4	1	1
<b>SP TECH®</b>											
Sodium Silicate (aq)	1	1	1	1	1	1	1	@	@	1	1
Sodium Sulfate (aq)	2	2	1	1	1	1	1	1	1	1	1
Sodium Thiosulfate (aq)	2	2	1	1	2	1	1	1	1	1	1
Soybean Oil	4	4	3	3	1	2	3	2	1	1	1
Stannic Chloride (aq)	1	1	1	1	1	2	1	@	2	1	1
<b>SP TECH®</b>											
Stannous Chloride (aq)	1	1	1	1	1	1	1	@	2	1	1
Steam Under 300°F	4	4	2	1	4	3	4	4	3	4	2
Steam Over 300°F	4	4	4	3	4	4	4	4	4	4	4
Stearic Acid	2	2	2	2	2	2	2	1	2	1	1
Stoddard Solvent	4	4	4	4	1	2	4	1	4	1	1
<b>SP TECH®</b>											
Styrene	4	4	4	4	4	4	4	3	4	1	1
Sucrose Solution	1	1	1	1	1	2	2	4	1	2	1
Sulfite Liquors	2	2	2	2	2	2	2	@	4	1	1
Sulfur	4	4	1	1	4	1	1	@	3	1	1
Sulfur Chloride (aq)	4	4	4	4	3	3	2	@	3	1	1
<b>SP TECH®</b>											
Sulfur Dioxide (Dry)	2	2	2	1	4	4	2	@	2	2	1
Sulfur Dioxide (Wet)	4	4	1	1	4	2	1	@	2	2	1
Sulfur Dioxide (Liquified Under Pressure)	4	4	2	1	4	4	4	@	2	2	1
Sulfur Hexafluoride	4	4	1	1	2	1	2	@	2	1	1

**SP TECH®**

**1** - рекомендовано

**2** - умеренное возд.

**3** - только в статике

**4** - не рекомендовано

@ - нет данных



	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPDM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
SP TECH®											
Sulfur Trioxide	2	2	2	2	4	4	4	@	2	1	1
Sulfuric Acid (Dilute)	3	3	2	2	3	2	1	3	4	1	1
Sulfuric Acid (Conc.)	4	4	4	3	4	4	1	4	4	1	1
Sulfuric Acid (20% Oleum)	4	4	4	4	4	4	4	4	4	1	1
Sulfurous Acid	2	2	2	2	2	2	1	3	4	3	2
SP TECH®											
Tannic Acid	1	2	1	1	1	1	1	1	2	1	1
Tar, Bituminous	4	4	3	3	2	3	4	@	2	1	1
Tartaric Acid	3	4	2	2	1	2	1	1	1	1	1
Terpineol	4	4	3	3	2	4	4	2	@	1	1
Tertiary Butyl Alcohol	2	2	2	2	2	2	2	4	2	1	1
SP TECH®											
Tertiary Butyl Catechol	4	2	2	2	4	2	2	4	@	1	1
Tertiary Butyl Mercaptan	4	4	4	4	4	4	@	4	4	1	1
Tetrabromoethane	4	4	4	4	4	4	@	@	4	1	1
Tetrabromomethane	4	4	4	4	4	4	@	@	4	1	1
Tetrabutyl Titanate	2	2	2	1	2	2	1	@	@	1	1
SP TECH®											
Tetrachloroethylene	4	4	4	4	4	4	4	4	4	1	1
Tetraethyl Lead	4	4	4	4	2	2	4	@	@	1	1
Tetrahydrofuran	4	4	3	3	4	4	4	3	4	4	4
Tetralin	4	4	4	4	4	4	4	@	4	2	1
Thionyl Chloride	4	4	4	3	4	4	4	4	@	2	1
SP TECH®											
Titanium Tetrachloride	4	4	4	4	2	4	4	4	4	1	1
Toluene	4	4	4	4	4	4	4	4	4	2	1
Toluene Diisocyanate	4	4	2	2	4	4	4	@	4	4	3
Transformer Oil	4	4	4	4	1	2	3	1	2	1	1
Transmission Fluid Type A	4	4	4	4	1	2	2	1	2	1	1

SP TECH®

1 - рекомендовано   
 2 - умеренное возд.   
 3 - только в статике   
 4 - не рекомендовано   
 @ - нет данных



	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPDM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
SP TECH®											
Triacetin	2	2	1	1	2	2	2	4	@	4	3
Triaryl Phosphate	4	4	1	1	4	4	4	4	3	1	1
Tributoxy Ethyl Phosphate	2	2	1	1	4	4	4	4	@	1	1
Tributyl Mercaptan	4	4	4	4	4	4	4	@	4	1	1
Tributyl Phosphate	2	4	2	2	4	4	4	4	4	4	4
SP TECH®											
Trichloroacetic Acid	3	2	2	2	2	4	4	4	@	4	3
Trichloroethane	4	4	4	4	4	4	4	4	4	1	1
Trichloroethylene	4	4	4	4	4	4	4	4	4	1	1
Tricresyl Phosphate	4	1	1	4	4	3	4	4	3	1	1
Triethanol Amine	2	2	2	1	2	1	2	4	@	4	4
SP TECH®											
Triethyl Aluminum	4	4	3	3	4	4	4	4	@	2	1
Triethyl Borane	4	4	3	3	4	4	4	4	@	1	1
Trinitrotoluene	4	4	4	4	4	2	2	@	@	2	1
Trioctyl Phosphate	4	4	1	1	4	4	4	4	3	2	1
Tung Oil (China Wood Oil)	4	4	3	3	1	2	3	3	4	1	1
SP TECH®											
Turbine Oil	4	4	4	4	2	4	4	1	4	1	1
Turpentine	4	4	4	4	1	4	4	4	4	1	1
Unsymmetrical Dimethyl Hydrazine (UDMH)	1	1	1	1	2	2	1	@	4	4	4
Varnish	4	4	4	4	2	4	4	3	4	1	1
SP TECH®											
Vegetable Oils	4	4	3	3	1	3	2	@	2	1	1
Versilube F-50	1	1	1	1	1	1	1	1	3	1	1
Vinegar	2	2	1	2	2	2	1	4	1	1	1
Vinyl Chloride	4	4	4	4	4	4	4	4	@	1	1
Wagner 21B Brake Fluid	2	1	2	1	3	2	2	@	3	4	3

SP TECH®

1 - рекомендовано

2 - умеренное возд.

3 - только в статике

4 - не рекомендовано

@ - нет данных



	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPDM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
SP TECH®											
Water	1	1	1	1	1	1	1	3	1	1	1
Whiskey, Wines	1	1	1	1	1	1	1	2	1	1	1
White Pine Oil	4	4	4	4	2	4	4	@	4	1	1
White Oil	4	4	4	4	1	2	4	1	4	1	1
Wood Oil	4	4	4	4	1	2	3	3	4	1	1
SP TECH®											
Xylene	4	4	4	4	4	4	4	4	4	1	1
Xylidine (Di-methyl Aniline)	3	3	3	2	3	3	4	4	4	4	3
Zeolites	1	1	1	1	1	1	1	@	@	1	1
Zinc Acetate (aq)	1	4	1	1	2	2	1	4	4	4	4
Zinc Chloride (aq)	1	1	1	1	1	1	1	1	1	1	1
SP TECH®											
Zinc Sulfate (aq)	2	2	1	1	1	1	1	@	1	1	1
TT-T-656b	4	4	1	1	4	4	4	4	4	4	@
VV-B-680	3	1	2	1	2	2	2	3	4	1	1
VV-G-632	4	4	4	4	1	1	1	1	3	1	1
VV-G-671c	4	4	4	4	1	1	1	1	3	1	1
SP TECH®											
VV-H-910	2	1	2	1	2	2	2	3	4	1	1
VV-I-530a	4	4	4	4	1	2	2	2	3	1	1
VV-K-211d	4	4	4	4	1	3	3	3	4	1	1
VV-K-220a	4	4	4	4	1	2	3	2	4	1	1
VV-L-751b	4	4	4	4	2	2	3	3	4	1	1
SP TECH®											
VV-L-800	4	4	4	4	1	2	2	2	3	1	1
VV-L-820b	4	4	4	4	1	2	2	2	3	1	1
VV-L-825a Type I	4	4	4	4	1	1	1	1	3	1	1
VV-L-825a Type II	4	4	4	4	1	1	1	1	3	1	1
VV-L-825a Type III	4	4	4	4	2	2	3	3	4	1	1

SP TECH®

1 - рекомендовано      2 - умеренное возд.      3 - только в статике      4 - не рекомендовано      @ - нет данных



		Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPDM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
		SP TECH®										
VV-O-526		4	4	4	4	1	1	1	1	3	1	1
VV-P-216a		4	4	4	4	1	2	2	2	3	1	1
VV-P-236		4	4	4	4	2	2	3	3	4	1	1
51-F-23		4	4	4	4	1	2	2	2	3	1	1
ASTM Method D-471	1	4	4	4	4	1	1	1	1	3	1	1
		SP TECH®										
ASTM Method D-471	2	4	4	4	4	1	2	2	2	3	1	1
ASTM Method D-471	3	4	4	4	4	1	2	2	2	3	1	1
MIL-L-644 B		3	3	3	3	1	3	3	3	3	@	@
MIL-L-2104 B		4	4	4	4	1	1	1	1	3	1	1
MIL-L-2105 B		4	4	4	4	1	1	1	1	3	1	1
		SP TECH®										
MIL-G-2108		4	4	4	4	1	1	1	1	3	1	1
MIL-S-3136 B Type I		4	4	4	4	1	2	3	2	4	1	1
MIL-S-3136 B Type II		4	4	4	4	1	3	3	3	4	1	1
MIL-S-3136 B Type III		4	4	4	4	1	3	3	3	4	1	1
MIL-S-3136 B Type IV		4	4	4	4	1	1	1	1	3	1	1
		SP TECH®										
MIL-S-3136 B Type V		4	4	4	4	1	2	2	2	3	1	1
MIL-S-3136 B Type VI		4	4	4	4	1	2	2	2	3	1	1
MIL-S-3136 B Type VII		4	4	4	4	1	3	3	3	4	1	1
MIL-L-3150 A		4	4	4	4	1	1	1	1	3	1	1
MIL-L-3503		4	4	4	4	1	2	2	2	3	1	1
		SP TECH®										
MIL-L-3545-B		4	4	4	4	2	2	3	3	4	1	1
MIL-C-4339 C		4	4	4	4	1	1	1	1	3	1	1
MIL-G-4343 B		4	4	3	3	2	2	2	1	4	1	1
MIL-L-5020 A		4	4	4	4	1	1	3	2	4	1	1
MIL-J-5161 F		4	4	4	4	1	3	3	3	4	1	1

SP TECH®

1 - рекомендовано    
 2 - умеренное возд.    
 3 - только в статике    
 4 - не рекомендовано    
 @ - нет данных





	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPDM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
<b>SP TECH®</b>											
MIL-C-5545 A	4	4	4	4	2	2	3	3	4	1	1
MIL-H-5559 A	2	1	1	1	1	2	2	3	2	2	1
MIL-F-5566	1	1	1	1	1	2	2	2	1	1	1
MIL-F-5602	4	4	4	4	1	2	2	2	3	1	1
MIL-H-5606 B (Red Oil)	4	4	4	4	1	2	2	1	4	1	1
<b>SP TECH®</b>											
MIL-J-5624 G JP-3, JP-4, JP-5	4	4	4	4	1	3	3	3	4	1	1
MIL-O-6081 C	4	4	4	4	1	2	2	2	3	1	1
MIL-L-6082 C	4	4	4	4	1	1	1	1	3	1	1
MIL-H-6083 C	4	4	4	4	1	2	2	2	3	1	1
MIL-L-6085 A	4	4	3	4	2	3	3	3	3	1	1
<b>SP TECH®</b>											
MIL-L-6086 B	4	4	4	4	1	1	1	1	3	1	1
MIL-L-6387 A	4	4	3	4	1	3	3	3	3	1	1
MIL-C-6529 C	4	4	4	4	2	2	3	2	4	1	1
MIL-F-7024 A	4	4	4	4	1	2	2	2	4	1	1
MIL-H-7083 A	2	1	1	1	1	2	2	3	2	2	1
<b>SP TECH®</b>											
MIL-G-7118 A	4	4	3	4	1	3	3	3	3	1	1
MIL-G-7187	4	4	4	4	1	1	1	1	3	1	1
MIL-G-7421 A	4	4	3	4	1	3	3	2	3	1	1
MIL-H-7644	2	1	2	1	2	2	2	3	4	1	1
MIL-L-7645	4	4	4	4	2	2	3	3	4	1	1
<b>SP TECH®</b>											
MIL-G-7711 A	4	4	4	4	1	1	1	1	3	1	1
MIL-L-7808 F	4	4	3	4	1	3	3	3	3	1	1
MIL-L-7870 A	4	4	4	4	1	2	2	2	3	1	1
MIL-C-8188 C	4	4	3	4	1	3	3	3	3	1	1
MIL-A-8243 B	2	1	1	1	1	2	2	3	2	@	1

**SP TECH®**

1 - рекомендовано   
 2 - умеренное возд.   
 3 - только в статике   
 4 - не рекомендовано   
 @ - нет данных



	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPDM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
SP TECH®											
MIL-L-8383 B	4	4	4	4	1	1	1	1	3	1	1
MIL-H-8446 B (MLO-8515)	4	4	4	4	2	2	1	4	4	1	1
MIL-1-8660 B	1	1	1	1	1	1	1	1	4	1	1
MIL-L-9000 F	4	4	4	4	1	2	3	3	4	1	1
MIL-T-9188 B	4	4	1	1	4	4	4	4	4	@	@
SP TECH®											
MIL-L-9236 B	3	3	3	3	1	3	3	2	4	1	1
MIL-L-10295 A	4	4	4	4	1	2	2	2	4	1	1
MIL-L-10324 A	4	4	4	4	1	2	2	2	3	1	1
MIL-G-10924 B	4	4	4	4	1	2	2	2	3	1	1
MIL-L-11734 B	4	4	3	4	1	3	3	3	3	1	1
SP TECH®											
MIL-O-11773	4	4	3	4	1	3	3	3	3	1	1
MIL-P-12098	2	1	2	1	2	2	2	3	4	1	1
MIL-H-13862	4	4	4	4	1	2	2	2	3	1	1
MIL-H-13866 A	4	4	4	4	1	2	2	2	3	1	1
MIL-H-13910 B	2	1	2	1	2	2	2	3	4	1	1
SP TECH®											
MIL-H-13919 A	4	4	4	4	4	2	2	2	3	1	1
MIL-L-14107 B	4	4	4	4	3	1	2	@	4	1	1
MIL-L-15017	4	4	4	4	1	1	1	1	3	1	1
MIL-L-15018 B	4	4	4	4	1	1	1	1	3	1	1
MIL-L-15019 C	4	4	4	4	1	1	1	1	3	1	1
SP TECH®											
MIL-L-15719 A	3	2	2	2	2	2	2	4	4	1	1
MIL-G-15793	4	4	3	4	1	3	3	3	3	1	1
MIL-F-16929 A	4	4	3	4	1	3	3	3	3	1	1
MIL-F-16958 A	4	4	4	4	1	2	2	2	3	1	1
MIL-F-17111	4	4	4	4	1	2	2	2	3	1	1

SP TECH®

1 - рекомендовано    2 - умеренное возд.    3 - только в статике    4 - не рекомендовано    @ - нет данных



	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPDM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
SP TECH®											
MIL-L-17331 D	4	4	4	4	1	1	1	1	3	1	1
MIL-L-17353 A	4	4	4	4	1	3	3	2	3	1	1
MIL-L-17672 B	4	4	4	4	1	1	1	1	3	1	1
MIL-L-18486 A	4	4	4	4	1	1	1	1	3	1	1
MIL-G-18709 A	4	4	4	4	1	1	1	1	3	1	1
SP TECH®											
MIL-H-19457 B	4	4	1	1	4	4	4	4	4	@	1
MIL-F-19605	4	4	4	4	1	3	3	3	4	1	1
MIL-L-19701	4	4	3	4	1	3	3	3	3	1	1
MIL-L-21260	4	4	4	4	1	1	1	1	3	1	1
MIL-L-21568 A	2	1	1	1	1	1	1	@	4	1	1
SP TECH®											
MIL-H-22072	2	1	1	1	1	2	2	3	2	2	1
MIL-L-22396	4	4	4	4	1	1	1	1	3	1	1
MIL-L-23699 A	4	4	3	4	1	3	3	3	3	1	1
MIL-G-23827 A	4	4	3	4	1	3	3	3	3	1	1
MIL-G-25013 D	2	1	1	1	1	2	2	3	4	1	1
SP TECH®											
MIL-F-25172	4	4	4	4	1	3	3	3	4	1	1
MIL-L-25336 B	4	4	3	4	1	3	3	3	3	1	1
MIL-F-25524 A	4	4	4	4	1	3	3	3	4	1	1
MIL-G-25537 A	4	4	4	4	1	2	2	2	3	1	1
MIL-F-25558 B (RJ-1)	4	4	4	4	1	2	2	1	3	1	1
SP TECH®											
MIL-F-25576 C (RP-1)	4	4	4	4	1	3	3	1	4	1	1
MIL-H-25598	4	4	4	4	1	2	2	2	3	1	1
MIL-F-25656 B	4	4	4	4	1	3	3	3	4	1	1
MIL-L-25681 C	2	1	1	1	1	2	2	3	4	1	1
MIL-G-25760 A	3	3	4	4	1	3	3	2	4	1	1

SP TECH®

1 - рекомендовано   
 2 - умеренное возд.   
 3 - только в статике   
 4 - не рекомендовано   
 @ - нет данных



	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPDM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
<b>SP TECH®</b>											
MIL-L-25968	4	4	4	4	1	3	3	3	3	1	1
MIL-L-26087 A	4	4	4	4	1	1	1	1	3	1	1
MIL-G-27343	1	1	1	1	1	1	1	1	4	1	1
MIL-H-27601 A	4	4	4	4	2	2	2	3	4	1	1
MIL-G-27617	@	2	1	1	4	@	@	@	4	1	1
<b>SP TECH®</b>											
MIL-I-27686 D	2	1	1	1	1	2	2	3	2	2	1
MIL-L-27694 A	1	1	1	1	1	1	1	1	4	1	1
MIL-L-46000 A	4	4	3	4	1	3	3	3	3	1	1
MIL-H-46001 A	4	4	4	4	1	1	1	1	3	1	1
MIL-L-46002	4	4	4	4	1	1	1	1	3	1	1
<b>SP TECH®</b>											
MIL-H-46004	4	4	4	4	1	2	2	2	3	1	1
MIL-P-46046 A	2	1	2	1	2	2	2	3	4	1	1
MIL-H-81019 B	4	4	4	4	1	2	2	2	3	1	1
MIL-S-81087	1	1	1	1	1	1	1	1	4	1	1
O-A-548 b	2	1	1	1	1	2	2	3	2	2	2
<b>SP TECH®</b>											
O-T-634 b	4	4	4	4	3	4	4	4	4	1	1
P-S-661 b	4	4	4	4	1	3	3	3	4	1	1
P-D-680	4	4	4	4	1	3	3	3	4	1	1
TT-N-95 a	4	4	4	4	1	3	3	3	4	1	1
TT-N-97 B	4	4	4	4	1	3	3	3	4	1	1
<b>SP TECH®</b>											
TT-I-735 b	1	1	1	1	1	2	2	2	1	1	1
TT-S-735 Type I	4	4	4	4	1	2	3	2	4	1	1
TT-S-735 Type II	4	4	4	4	1	3	3	3	4	1	1
TT-S-735 Type III	4	4	4	4	1	3	3	3	4	1	1
TT-S-735 Type IV	4	4	4	4	1	1	1	1	3	1	1

**SP TECH®**

1 - рекомендовано   
 2 - умеренное возд.   
 3 - только в статике   
 4 - не рекомендовано   
 @ - нет данных



TT-S-735 Type V

TT-S-735 Type VI

TT-S-735 Type VII

	Natural (NR, IR)	Commercial (SBR, BR)	Butyl (IIR)	EPDM (EPDM)	Nitrile (NBR)	Neoprene (CR)	Hypalon (CSM)	Polyurethane (EU, AU)	Silicone (SI)	FKM (Type 1)	FKM (Type 2)
SP TECH®	4	4	4	4	1	2	2	2	3	1	1
	4	4	4	4	1	2	2	2	3	1	1
	4	4	4	4	1	4	4	3	4	1	1

SP TECH®

1 - рекомендовано

2 - умеренное возд.

3 - только в статике

4 - не рекомендовано

@ - нет данных